

XANTAR[®] C RC 3720

Property Data

(PC+ABS)...

Vicat 120°C, Black color only, Improved Impact

Properties	Typical Data	Unit	Test Method
RHEOLOGICAL PROPERTIES			
Melt volume-flow rate	12	cm ³ /10min	ISO 1133
Temperature	260	°C	ISO 1133
Load	5	kg	ISO 1133
Molding shrinkage (parallel)	0.6	%	ISO 294-4
MECHANICAL PROPERTIES			
Tensile modulus	2200	MPa	ISO 527-1/-2
Yield stress	50	MPa	ISO 527-1/-2
Yield strain	4	%	ISO 527-1/-2
Nominal strain at break	>50	%	ISO 527-1/-2
Flexural modulus	2250	MPa	ISO 178
Flexural strength	80	MPa	ISO 178
Charpy impact strength (+23°C)	N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	60	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	25	kJ/m ²	ISO 179/1eA
Izod notched impact strength (23°C)	50	kJ/m ²	ISO 180/4A
Izod notched impact strength (-20°C)	30	kJ/m ²	ISO 180/4A
Puncture energy (+23°C)	35	J	ISO 6603-2
Puncture energy, part with rib (+23°C)	25	J	DSM (ISO 6603-2 based)
Puncture energy, part with rib (-20°C)	10	J	DSM (ISO 6603-2 based)
THERMAL PROPERTIES			
Temp. of deflection under load (1.80 MPa)	102	°C	ISO 75-1/-2
Vicat softening temperature (50°C/h 50N)	122	°C	ISO 306
Coeff. of linear therm. expansion (parallel)	0.7	E-4/°C	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	0.7	E-4/°C	ISO 11359-1/-2
ELECTRICAL PROPERTIES			
Relative permittivity (1GHz)	2.8	-	IEC 60250
Volume resistivity	>1E13	Ohm*m	IEC 60093
Surface resistivity	>1E15	Ohm	IEC 60093
OTHER PROPERTIES			
Water absorption	0.6	%	Sim. to ISO 62
Density	1190	kg/m ³	ISO 1183

01.12.2009

All information supplied by or on behalf of Mitsubishi Engineering-Plastics Corporation in relation to its products, whether in the nature of data, recommendations or otherwise, is supported by research and, in good faith, believed reliable, but Mitsubishi Engineering-Plastics Corporation assumes no liability and makes no warranties of any kind, express or implied, including, but not limited to, those of title, merchantability, fitness for a particular purpose or non-infringement or any warranty arising from a course of dealing, usage, or trade practice whatsoever in respect of application, processing or use made of the aforementioned information or product. The user assumes all responsibility for the use of all information provided and shall verify quality and other properties or any consequence from the use of all such information. Typical values are indicative only and are not to be construed as being binding specifications.