

Product Description

CAPILENE® QU 80 A is a polypropylene random copolymer intended for transparent thin wall injection molded articles.

Features:	<ul style="list-style-type: none"> • Clarified • Mold release • Good organoleptic properties 	<ul style="list-style-type: none"> • High flow • Short cycle time
Uses:	<ul style="list-style-type: none"> • Thin wall packaging • Food packaging 	<ul style="list-style-type: none"> • Household articles • Toys
Processing Methods:	<ul style="list-style-type: none"> • Injection molding 	

Properties		Method	Typical Value*	Unit
Physical				
Melt Flow Rate	(230°C/2.16 kg)	ISO 1133	35	g/10 min
Mechanical				
Tensile Stress at Yield	(50 mm/min)	ISO 527-2	25	MPa
Tensile Strain at Yield	(50 mm/min)	ISO 527-2	13	%
Flexural Modulus	(5 mm/min)	ISO 178	1100	MPa
Izod Impact Strength, notched	(+23°C)	ISO 180	4	kJ/m ²
Thermal				
Vicat Softening Temperature	(10 N)	ISO 306	130	°C
Heat Deflection Temperature	(0.45 MPa)	ISO 75-2	75	°C
Optical				
Haze	(1 mm plaque)	ASTM D1003	10	%

*Typical values; not to be construed as specifications.

Health, Quality, Regulations and Safety

This product is not classified as dangerous substance. Material safety data sheets, international standards certificates (e.g. ISO 9001) and other regulatory documents are available on our website. This product is not intended for use in medical or pharmaceutical applications and we do not support its use for such applications.